

Thermoplastics pipes — Universal wall thickness table

ICS 23.040.20

NO COPYING WITHOUT BSI PERMISSION EXCEPT AS PERMITTED BY COPYRIGHT LAW



National foreword

This British Standard reproduces verbatim ISO 4065:1996 and implements it as the UK national standard.

The UK participation in its preparation was entrusted to Technical Committee PRI/61, Plastics piping systems and components, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the BSI Standards Catalogue under the section entitled “International Standards Correspondence Index”, or using the “Find” facility of the BSI Standards Electronic Catalogue.

This British Standard partially supersedes BS 5556:1978: in particular, Table 4 of ISO 4065:1996 corresponds to but is not identical with Table 4 of BS 5556:1978. Hence for existing standards which refer specifically to BS 5556, that reference still applies until changed by amendment, revision or agreement to make reference to BS ISO 4065 or ISO 4065. For fresh applications, BS 5556 should be regarded as obsolescent for the purposes covered by BS ISO 4065, which should be referred to accordingly.

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, pages i and ii, the ISO title page, page ii, pages 1 to 6, an inside back cover and a back cover. This standard has been updated (see copyright date) and may have had amendments incorporated. This will be indicated in the amendment table on the inside front cover.

This British Standard, having been prepared under the direction of the Sector Board for Materials and Chemicals, was published under the authority of the Standards Board and comes into effect on 15 May 1997

© BSI 09-1999

ISBN 0 580 27501 9

Amendments issued since publication

Amd. No.	Date	Comments

Contents

	Page
National foreword	Inside front cover
Foreword	ii
1 Scope	1
2 Normative reference	1
3 Definitions	1
4 Calculation of wall-thickness values	1
5 Wall-thickness tables	2
6 Non-pressure pipes	2
7 Deviations	2
Annex A (informative) Bibliography	Inside back cover
Table 1 — Individual S-values calculated from selected values of design stress, $\bar{\sigma}_s$, and maximum allowable operating pressure, p_{PMS}	3
Table 2 — Nominal S-values and their calculated values, taken from ISO 497 for p_{PMS} values of 2; 2,5; 3,15; 4; 6,3; 8; 10; 12,5; 16; 20 and 25 bar	3
Table 3 — S-values and design stresses taken from Table 1 for the calculation of wall thicknesses for the p_{PMS} value of 6 bar	3
Table 4 — Nominal wall thickness, e_n , for p_{PMS} values of 2,5; 3,15; 4; 5; 6,3; 8; 10; 12,5; 16; 20 and 25 bar	4
Table 5 — Nominal wall thickness, e_n , for a p_{PMS} value of 6 bar	6



INTERNATIONAL STANDARD

**ISO
4065**

Second edition
1996-12-15

Thermoplastics pipes — Universal wall thickness table

*Tubes en matières thermoplastiques — Tableau universel des épaisseurs
de paroi*



Reference number
ISO 4065:1996(E)

This document is now
PUBLIC

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 4065 was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*.

This second edition cancels and replaces the first edition (ISO 4065:1978), which has been technically revised.

The aim of the first edition was to identify a series of standard wall thicknesses for thermoplastics pipes as a means of controlling the wide variety of wall thicknesses which might otherwise be produced. The revision of this document has resulted in a number of basic changes. The standard now provides a basis for establishing a series of wall thicknesses for use in the preparation of product standards.

However, it is not regarded as providing an exclusive list of wall thicknesses, as there may be occasions when specific applications require other wall thicknesses to take into account additional factors such as stiffness or temperature conditions.

Annex A of this International Standard is for information only.

Descriptors: Plastics products, pipes (tubes), thermoplastic resins, plastic tubes, dimensions, diameters, thickness

1 Scope

This International Standard specifies the relationship between the nominal wall thickness e_n and the nominal outside diameter d_n of thermoplastics pipes.

It is applicable to smooth thermoplastics pipes of constant circular cross-section along the whole length of the pipe, whatever their method of manufacture, their composition or their intended application.

2 Normative reference

The following standard contains provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the edition indicated was valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent edition of the standard indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 3:1973, *Preferred numbers — Series of preferred numbers*.

3 Definitions

For the purposes of this International Standard, the following definitions apply.

3.1

nominal outside diameter, d_n

a numerical designation of size which is common to all components in a thermoplastics piping system other than flanges and components designated by thread size. It is a convenient round number for reference purposes

NOTE 1 For metric pipe series conforming to ISO 161-1 [1] (see Annex A), the nominal outside diameters, expressed in millimetres, are the minimum mean outside diameters $d_{em,min}$ in the applicable standard for pipe.

3.2

mean outside diameter, d_{em}

the measured length of the outer circumference of the pipe divided by π , rounded to the next higher 0,1 mm

3.3

wall thickness at any point, e_y

the measured wall thickness at any point around the circumference of the pipe, rounded to the next higher 0,1 mm

3.4

nominal wall thickness, e_n

a wall thickness tabulated in this International Standard, and identical to the minimum permissible wall thickness at any point, $e_{y,min}$

3.5

standard dimension ratio, SDR

the ratio of the nominal outside diameter d_n of a pipe to its nominal wall thickness e_n

NOTE 2 This value may also be derived from the equation given in 3.6.

3.6

pipe series, S

a dimensionless number related to the nominal outside diameter d_n and nominal wall thickness e_n , the value of which is as specified in the tables in this International Standard

the pipe series-number S is given by the following equation

$$S = \frac{SDR - 1}{2}$$

and for pressure pipes this can be expressed as:

$$S = \frac{B}{p}$$

where

p is the internal pressure;

σ is the induced stress;

p and σ being expressed in the same units.

for the selection of p and σ , the reader is referred to ISO 161-1[1]

S-values equal to or less than 10 are selected from the R 10 series of preferred numbers given in ISO 3, whilst those greater than 10 are selected from the R 20 series

4 Calculation of wall-thickness values

According to ISO 161-1, wall thicknesses for pressure pipes are calculated from either of the following equations:

$$e_n = \frac{1}{2 \frac{\sigma}{p} + 1} \times d_n$$

and

$$e_n = \frac{1}{2S + 1} \times d_n$$

¹⁾ The value of π is taken to be 3,142.

where

- e_n is the nominal wall thickness;
- d_n is the nominal outside diameter;
- e_n and d_n being expressed in the same units;
- $\hat{\sigma}$ is the induced stress;
- p is the internal pressure;
- $\hat{\sigma}$ and p being expressed in the same units;
- S is the series number.

The general equations are also applicable to the relationship between the maximum allowable operating pressure p_{PMS} and the design stress $\hat{\sigma}_s$, as follows:

$$e_n = \frac{1}{2 \frac{\hat{\sigma}_s}{p_{PMS}} + 1} \times d_n$$

Values for p_{PMS} are selected from the R 10 series of preferred numbers given in ISO 3.

Values for $\hat{\sigma}_s$ equal to or less than 10 MPa are selected from the R 10 series of preferred numbers given in ISO 3, whilst those greater than 10 MPa are selected from the R 20 series.

S may therefore be defined as the quotient of the design stress and the maximum allowable operating pressure as follows:

$$S = \frac{B_s}{p_{PMS}}$$

For maximum allowable operating pressures between 2,5 bar and 25 bar and design stresses between 2,5 MPa and 16 MPa, the corresponding S values are given in Table 1. This table also incorporates an additional pipe series based on a nominal pressure of 6 bar which is not a preferred number of the R 10 series. This maximum allowable operating pressure has been included in Table 1 because it is used in many countries in preference to the value of 6,3 bar.

Table 2 gives the calculated values of S taken from ISO 497[2], and Table 3 gives calculated values of S for a p_{PMS} of 6 bar.

NOTE 3 With the exception of the 6 bar series, S is the quotient of two R 10 numbers for design stresses of 10 MPa and below, and therefore it is itself a number of the R 10 series also. For values greater than 10 MPa, S is the quotient of an R 10 and an R 20 number, and therefore in this case the number is an R 20 value. This is the key to the reduction in the many theoretical combinations of design stress and operating pressure to a practical selection of values of S . Since preferred numbers are themselves rounded off from the theoretical values, quotients of preferred numbers cannot basically be identical either with preferred numbers or with the theoretical values.

These theoretical values may, however, be considered as mean values for all corresponding quotients. Therefore, a universal wall thickness table which is mathematically based on the theoretical values of the R 10 and R 20 series of preferred numbers for S guarantees a minimum number of deviations from the numerous theoretical wall thicknesses.

NOTE 4 All calculated values of wall thickness given in Table 4 and Table 5 have been rounded off to one significant figure using the following procedure:

Step 1: Express the calculated value to three significant figures, e.g. 0,XXX.

Step 2:

- a) If the second significant figure is 1 or higher, then the first significant figure is rounded up.
- b) If the second significant figure is 0 and the third significant figure is 5 or over, then the first significant figure is rounded up, but if the third significant figure is 4 or less, then the value is rounded down by expressing the value as the first significant figure.

5 Wall-thickness tables

Table 4 gives the relationship between the nominal wall thickness e_n and the nominal outside diameter d_n based on the S -values given in Table 2.

The wall thicknesses of an additional pipe series based on a maximum permissible operating pressure of 6 bar are given in Table 5, and are calculated from the S -values given in Table 3.

6 Non-pressure pipes

Although the calculation of the wall thickness with the value of S derived from the quotient of the design stress $\hat{\sigma}_s$ and a maximum allowable operating pressure p_{PMS} which applies to pipes predominantly subject to internal hydrostatic pressure, the values given in Table 4 and Table 5 also apply to pipes not subject to internal pressure.

7 Deviations

Notwithstanding the generalities expressed in clause 6, it is appreciated that there may be some occasions when specific applications require other wall thicknesses in order to take into account additional factors such as stiffness or temperature conditions. It is strongly recommended that such exceptions are kept to a minimum, however.

This document is now
PUBLIC

Table 1 — Individual S-values calculated from selected values of design stress, σ_s , and maximum allowable operating pressure, p_{PMS}

Design stress σ_s MPa	p_{PMS} bar											
	25	20	16	12,5	10	8	6,3	6	5	4	3,15	2,5
S-values												
16	6,400 0	8,000 0	10,000	12,800	16,000	20,000	25,397	26,667	32,000	40,000	50,794	64,000
14	5,600 0	7,000 0	8,750 0	11,200	14,000	17,000	22,222	23,333	28,000	35,000	44,444	56,000
12,5	5,000 0	6,250 0	7,812 5	10,000	12,500	15,625	19,841	20,833	25,000	31,250	39,683	50,000
11,2	4,480 0	5,600 0	7,000 0	8,960 0	11,200	14,000	17,778	18,667	22,400	28,000	35,556	44,800
10	4,000 0	5,000 0	6,250 0	8,000 0	10,000	12,500	15,873	16,667	20,000	25,000	31,746	40,000
8	3,200 0	4,000 0	5,000 0	6,400 0	8,000 0	10,000	12,698	13,333	16,000	20,000	25,397	32,000
6,3	2,520 0	3,150 0	3,937 5	5,040 0	6,300 0	7,875 0	10,000	10,500	12,600	15,750	20,000	25,200
5	2,000 0	2,500 0	3,125 0	4,000 0	5,000 0	6,250 0	7,936 5	8,333 3	10,000	12,500	15,873	20,000
4		2,000 0	2,500 0	3,200 0	4,000 0	5,000 0	6,439 2	6,666 7	8,000 0	10,000	12,698	16,000
3,15			1,968 8	2,150 0	3,150 0	3,937 5	5,000 0	5,250 0	6,300 0	7,875 0	10,000	12,600
2,5				2,000 0	2,000 0	3,125 0	3,968 3	4,166 7	5,000 0	6,250 0	7,936 5	10,000

NOTE Individual S-values below 2,000 0 have been excluded from this table as the resulting pipe geometry is considered to be unacceptable for practical applications.

Table 2 — Nominal S-values and their calculated values, taken from ISO 497 for p_{PMS} values of 2; 2,5; 3,15; 4; 5; 6,3; 8; 10; 12,5; 16; 20 and 25 bar^a

Nominal S-values	Calculated values
2	1,995 3
2,5	2,511 9
3,2	3,162 3
4	3,981 1
5	5,011 9
6,3	6,309 6
8	7,943 3
10	10,000
11,2	11,220
12,5	12,589
14	14,125
16	15,849
20	19,953
25	25,119
32	31,623
40	39,811
50	50,119
63	63,096

^a Higher values shall be taken from R 10 series of numbers given in ISO 3.

Table 3 — S-values and design stresses, taken from Table 1 for the calculation of wall thicknesses for the p_{PMS} value of 6 bar

Design stress MPa	Calculated S-values	Nominal S-values
2,5	4,166 7	4,2
3,15	5,250 0	5,3
4	6,666 7	6,7
5	8,333 3	8,3
6,3	10,500	10,5
8	13,333	13,3
10	16,667	16,7
11,2	18,667	18,7
12,5	20,833	20,8
14	23,333	23,3
16	26,667	26,7

Table 4 — Nominal wall thickness, e_n , for p_{PMS} values of 2,5; 3,15; 4; 5; 6,3; 8; 10; 12,5; 16; 20 and 25 bar

Dimensions in millimetres

Nominal outside diameter, d_n	Pipe series S (Standard dimension ratio SDR)																	
	2	2,5	3,2	4	5	6,3	8	10	11,2	12,5	14	16	20	25	32	40	50	63
	(5)	(6)	(7,4)	(9)	(11)	(13,6)	(17)	(21)	(23,4)	(26)	(29)	(33)	(41)	(51)	(65)	(81)	(101)	(127)
	Nominal wall thickness, e_n																	
2,5	0,5																	
3	0,6	0,5	0,5															
4	0,8	0,7	0,6	0,5														
5	1,0	0,9	0,7	0,6	0,5													
6	1,2	1,0	0,9	0,7	0,6	0,5												
8	1,6	1,4	1,1	0,9	0,8	0,6	0,5											
10	2,0	1,7	1,4	1,2	1,0	0,8	0,6	0,5	0,5									
12	2,4	2,0	1,7	1,4	1,1	0,9	0,8	0,6	0,6	0,5	0,5							
16	3,3	2,7	2,2	1,8	1,5	1,2	1,0	0,8	0,7	0,7	0,6	0,5						
20	4,1	3,4	2,8	2,3	1,9	1,5	1,2	1,0	0,9	0,8	0,7	0,7	0,5					
25	5,1	4,2	3,5	2,8	2,3	1,9	1,5	1,2	1,1	1,0	0,9	0,8	0,7	0,5				
32	6,5	5,4	4,4	3,6	2,9	2,4	1,9	1,6	1,4	1,3	1,1	1,0	0,8	0,7	0,5			
40	8,1	6,7	5,5	4,5	3,7	3,0	2,4	1,9	1,8	1,6	1,4	1,3	1,0	0,8	0,7	0,5		
50	10,1	8,3	6,9	5,6	4,6	3,7	3,0	2,4	2,2	2,0	1,8	1,6	1,3	1,0	0,8	0,7	0,5	
63	12,7	10,5	8,6	7,1	5,8	4,7	3,8	3,0	2,7	2,5	2,2	2,0	1,6	1,3	1,0	0,8	0,7	0,5
75	15,1	12,5	10,3	8,4	6,8	5,6	4,5	3,6	3,2	2,9	2,6	2,3	1,9	1,5	1,2	1,0	0,8	0,6
90	18,1	15,0	12,3	10,1	8,2	6,7	5,4	4,3	3,9	3,5	3,1	2,8	2,2	1,8	1,4	1,2	0,9	0,8
110	22,1	18,3	15,1	12,3	10,0	8,1	6,6	5,3	4,7	4,2	3,8	3,4	2,7	2,2	1,8	1,4	1,1	0,9
125	25,1	20,8	17,1	14,0	11,4	9,2	7,4	6,0	5,4	4,8	4,3	3,9	3,1	2,5	2,0	1,6	1,3	1,0
140	28,1	23,3	19,2	15,7	12,7	10,3	8,3	6,7	6,0	5,4	4,8	4,3	3,5	2,8	2,2	1,8	1,4	1,1
160	32,1	26,6	21,9	17,9	14,6	11,8	9,5	7,7	6,9	6,2	5,5	4,9	4,0	3,2	2,5	2,0	1,6	1,3
180	36,1	29,9	24,6	20,1	16,4	13,3	10,7	8,6	7,7	6,9	6,2	5,5	4,4	3,6	2,8	2,3	1,8	1,5
200	40,1	33,2	27,4	22,4	18,2	14,7	11,9	9,6	8,6	7,7	6,9	6,2	4,9	3,9	3,2	2,5	2,0	1,6
225	45,1	37,4	30,8	25,2	20,5	16,6	13,4	10,8	9,6	8,6	7,7	6,9	5,5	4,4	3,5	2,8	2,3	1,8
250	50,1	41,5	34,2	27,9	22,7	18,4	14,8	11,9	10,7	9,6	8,6	7,7	6,2	4,9	3,9	3,1	2,5	2,0

Table 4 — Nominal wall thickness, e_n , for p_{PMS} values of 2,5; 3,15; 4; 5; 6,3; 8; 10; 12,5; 16; 20 and 25 bar

Dimensions in millimetres

Nominal outside diameter, d_n	Pipe series S (Standard dimension ratio SDR)																	
	2	2,5	3,2	4	5	6,3	8	10	11,2	12,5	14	16	20	25	32	40	50	63
	(5)	(6)	(7,4)	(9)	(11)	(13,6)	(17)	(21)	(23,4)	(26)	(29)	(33)	(41)	(51)	(65)	(81)	(101)	(127)
	Nominal wall thickness, e_n																	
280	56,2	46,5	38,3	31,3	25,4	20,6	16,6	13,4	12,0	10,7	9,6	8,6	6,9	5,5	4,4	3,5	2,8	2,2
315		52,3	43,1	35,2	28,6	23,2	18,7	15,0	13,5	12,1	10,8	9,7	7,7	6,2	4,9	4,0	3,2	2,5
355		59,0	48,5	39,7	32,2	26,1	21,1	16,9	15,2	13,6	12,2	10,9	8,7	7,0	5,6	4,4	3,6	2,8
400			54,7	44,7	36,3	29,4	23,7	19,1	17,1	15,3	13,7	12,3	9,8	7,9	6,3	5,0	4,0	3,2
450			61,5	50,3	40,9	33,1	26,7	21,5	19,2	17,2	15,4	13,8	11,0	8,8	7,0	5,6	4,5	3,6
500				55,8	45,4	36,8	29,7	23,9	21,4	19,1	17,1	15,3	12,3	9,8	7,8	6,2	5,0	4,0
560					50,8	41,2	33,2	26,7	23,9	21,4	19,2	17,2	13,7	11,0	8,8	7,0	5,6	4,4
630					57,2	46,3	37,4	30,0	26,9	24,1	21,6	19,3	15,4	12,3	9,9	7,9	6,3	5,0
710						52,2	42,1	33,9	30,3	27,2	24,3	21,8	17,4	13,9	11,1	8,9	7,1	5,6
800						58,8	47,4	38,1	34,2	30,6	27,4	24,5	19,6	15,7	12,5	10,0	7,9	6,3
900							53,3	42,9	38,4	34,4	30,8	27,6	22,0	17,6	14,1	11,2	8,9	7,1
1 000							59,3	47,7	42,7	38,2	34,2	30,6	24,5	19,6	15,6	12,4	9,9	7,9
1 200								57,2	51,2	45,9	41,1	36,7	29,4	23,5	18,7	14,9	11,9	9,5
1 400										53,5	47,9	42,9	34,3	27,4	21,8	17,4	13,9	11,1
1 600										61,2	54,7	49,0	39,2	31,3	24,9	19,9	15,8	12,6
1 800											61,6	55,1	44,0	35,2	28,1	22,4	17,8	14,2
2 000											68,4	61,2	48,9	39,1	31,2	24,9	19,8	15,8

This document is now
PUBLIC

Table 5 — Nominal wall thicknesses, e_n , for a p_{PMS} value of 6 bar

Dimensions in millimetres

Nominal outside diameter, d_n	Pipe series S (Standard dimension ratio SDR)										
	4,2 (9,4)	5,3 (11,6)	6,7 (14,4)	8,3 (17,6)	10,5 (22)	13,3 (27,6)	16,7 (34,4)	18,7 (38,4)	20,8 (42,6)	23,3 (47,6)	26,7 (54,4)
	Nominal wall thickness, e_n										
2,5											
3											
4	0,5										
5	0,6	0,5									
6	0,7	0,6	0,5								
8	0,9	0,7	0,6	0,5							
10	1,1	0,9	0,7	0,6	0,5						
12	1,3	1,1	0,9	0,7	0,6	0,5					
16	1,8	1,4	1,2	1,0	0,8	0,6	0,5	0,5			
20	2,2	1,8	1,4	1,2	1,0	0,8	0,6	0,6	0,5	0,5	
25	2,7	2,2	1,8	1,5	1,2	0,9	0,8	0,7	0,6	0,6	0,5
32	3,5	2,8	2,3	1,9	1,5	1,2	1,0	0,9	0,8	0,7	0,6
40	4,3	3,5	2,8	2,3	1,9	1,5	1,2	1,1	1,0	0,9	0,8
50	5,4	4,4	3,5	2,9	2,3	1,9	1,5	1,3	1,2	1,1	1,0
63	6,8	5,5	4,4	3,6	2,9	2,3	1,9	1,7	1,5	1,4	1,2
75	8,1	6,6	5,3	4,3	3,5	2,8	2,2	2,0	1,8	1,6	1,4
90	9,7	7,9	6,3	5,1	4,1	3,3	2,7	2,4	2,2	1,9	1,7
110	11,8	9,6	7,7	6,3	5,0	4,0	3,2	2,9	2,6	2,4	2,1
125	13,4	10,9	8,8	7,1	5,7	4,6	3,7	3,3	3,0	2,7	2,3
140	15,0	12,2	9,8	8,0	6,4	5,1	4,1	3,7	3,3	3,0	2,6
160	17,2	14,0	11,2	9,1	7,3	5,8	4,7	4,2	3,8	3,4	3,0
180	19,3	15,7	12,6	10,2	8,2	6,6	5,3	4,7	4,3	3,8	3,4
200	21,5	17,4	14,0	11,4	9,1	7,3	5,9	5,3	4,7	4,2	3,7
225	24,2	19,6	15,7	12,8	10,3	8,2	6,6	5,9	5,3	4,8	4,2
250	26,8	21,8	17,5	14,2	11,4	9,1	7,3	6,6	5,9	5,3	4,6
280	30,0	24,4	19,6	15,9	12,8	10,2	8,2	7,3	6,6	5,9	5,2
315	33,8	27,4	22,0	17,9	14,4	11,4	9,2	8,3	7,4	6,7	5,8
355	38,1	30,9	24,8	20,1	16,2	12,9	10,4	9,3	8,4	7,5	6,6
400	42,9	34,8	28,0	22,7	18,2	14,5	11,7	10,5	9,4	8,4	7,4
450	48,3	39,2	31,4	25,5	20,5	16,3	13,2	11,8	10,6	9,5	8,3
500	53,6	43,5	34,9	28,3	22,8	18,1	14,6	13,1	11,8	10,5	9,2
560	60,0	48,7	39,1	31,7	25,5	20,3	16,4	14,7	13,2	11,8	10,4
630		54,8	44,0	35,7	28,7	22,8	18,4	16,5	14,8	13,3	11,6
710			49,6	40,2	32,3	25,7	20,7	18,6	16,7	14,9	13,1
800			55,9	45,3	36,4	29,0	23,3	20,9	18,8	16,8	14,8
900				51,0	41,0	32,6	26,3	23,5	21,1	18,9	16,6
1 000				56,6	45,5	36,2	29,2	26,1	23,5	21,0	18,4
1 200					54,6	43,4	35,0	31,3	28,2	25,2	22,1
1 400						50,6	40,8	36,6	32,9	29,4	25,8
1 600						57,9	46,6	41,8	37,5	33,6	29,5
1 800							52,5	47,0	42,2	37,8	33,2
2 000							58,3	52,2	46,9	42,0	36,9

Annex A (informative)

Bibliography

- [1] ISO 161-1:1996, *Thermoplastics pipes for the conveyance of fluids — Nominal outside diameters and nominal pressures — Part 1: Metric series*.
- [2] ISO 497:1973, *Guide to the choice of series of preferred numbers and of series containing more rounded values of preferred numbers*.
- [3] ISO 2944:1974, *Fluid power systems and components — Nominal pressures*.
- [4] ISO 3126:1974, *Plastics pipes — Measurement of dimensions*.
- [5] ISO 11922-1:—, *Thermoplastics pipes for the conveyance of fluids — Dimensions and tolerances — Part 1: Metric series*²⁾.

²⁾ To be published. (Revision of ISO 3606:1976, ISO 3607:1977, ISO 3608:1976 and ISO 3609:1977)

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: 0181 996 9000. Fax: 0181 996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: 0181 996 7000. Fax: 0181 996 7001.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: 0181 996 7111. Fax: 0181 996 7048.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: 0181 996 7002. Fax: 0181 996 7001.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

If permission is granted, the terms may include royalty payments or a licensing agreement. Details and advice can be obtained from the Copyright Manager. Tel: 0181 996 7070.

BSI
389 Chiswick High Road
London
W4 4AL